

Innothane®

Product Name

InnoClear™ OC-7086
Water Clear/Rigid

Description

OC-7086 is a water-clear, rigid polyurethane formulated for room temperature hand-batch or vacuum assisted casting methods. Excellent physical properties can be obtained with a room temperature cure without the utilization of mercury, MOCA, or TDI. The unique chemistry allows for excellent optical clarity as well as U.V. protection. Mixed material can be cast into either tin or platinum silicone molds.

Physical Properties

Mix Ratio	Resin:Hardener (parts by weight)		100:57
Mix Ratio	Resin:Hardener (parts by volume)		100:59
Viscosity (cps@77°F)	Resin	450	Gel Time
	Hardener	1300	
	Mixed	650	Demold Time*
			17.5 ± 2.5 Minutes
			3 ± 1 Hours
Specific Gravity (g/cc)	Resin	1.13	Color
	Hardener	1.10	
			Water Clear

* Demold time is always mass dependant

Cured Properties

Cure 1 ► 24 hours at 77°F + 4 hours at 150°F
 Cure 2 ► 7 days at 77°F



	Method	Cure 1	Cure 2
Hardness (shore D)	ASTM D-2240	80 ± 5	80 ± 5
Tensile Strength (psi)	ASTM D-638	10,500	8,000
Elongation at Break	ASTM D-638	8%	8%
Ultimate Flex Strength (psi)	ASTM D-790	16,000	14,000
Tensile Modulus (psi)	ASTM D-638	265,000	270,000
Flexural Modulus (psi)	ASTM D-790	345,000	350,000
Notched Izod (ft.lbs./in.)	ASTM D-256	1.1	0.5
Linear Shrink (in./in.)	ASTM D-2566	.001-.005	.001-.005
Heat Deflection Temp. (66psi)	ASTM D-648	95°C / 203°F	54°C / 129°F
Heat Deflection Temp. (264psi)	ASTM D-648	91°C / 196°F	N/A
Specific Gravity (g/cc)		1.10	1.10

Processing Notes

For best results, de-air the material prior to casting, then pressurize to 60 psi until cured. However, if pressure cannot be used, this material has been designed for vacuum degas only. OC-7086 can be easily buffed when cured.

<u>Kit Weights</u>	Quart Kit	1 Gal. Kit	5 Gal. Kit	Drum Kit
	3.14 lbs.	12.56 lbs.	62.8 lbs.	706.5 lbs.

Safety and Handling

Although warming the hardener will reduce the viscosity effectively, it is not recommended that the material be stored in the oven at 100°F or above. This will cause the material to yellow.

DO NOT USE UNTIL MSDSs HAVE BEEN READ AND UNDERSTOOD. Store containers in a dry location. Partially used containers should be blanketed with dry nitrogen to prevent moisture contamination. Moisture will react with the resin component, creating carbon dioxide gas and a possible pressure increase in the container.

SPECIFICATION WRITERS: The above values are meant to represent typical properties only. Users are encouraged to qualify products in their own laboratories prior to specification publication.

PURCHASER has the responsibility for determining any applicability of and compliance with federal, state, and local laws concerning labeling, use, and waste disposal, particularly in making consumer items. Innovative Polymers, Inc. makes no warranty, expressed or implied, for merchantability or fitness of use. The sole liability of Innovative Polymers, Inc. for any claim arising out of the manufacture, use, or sale of its products shall be the buyers purchase price.